arXiv:1803.03408v1 [cond-mat.soft] 9 Mar 2018

On Scott-Blair model with time-varying viscosity in linear viscoelasticity

Roberto GARRA[1] and Francesco MAINARDI[2]

[1] University of Rome La Sapienza, Dipartimento di Scienze Statistiche,
P. le A. Moro 5, 00185 Roma, ITALY
roberto.garra@sbai.uniroma1.it

[2] University of Bologna and INFN, Department of Physics & Astronomy (DIFA),
Via Irnerio 46, 40126 Bologna, ITALY
Corresponding author; e-mail: francesco.mainardi@bo.infn.it

Abstract

In a recent paper, Zhou et al. [15] studied the time-dependent properties of Glass Fiber Reinforced Polymers (GFRP) composites by using a new rheological model with a time-variable viscosity coefficient. This rheology is essentially based on a generalized Scott-Blair model with time-varying viscosity coefficient involving Riemann-Liouville fractional derivatives. Motivated by this study, in this note we suggest a different generalization of the Scott-Blair model based on the application of Caputo fractional derivatives of a function with respect to another function. This new mathematical approach can be useful in viscoelasticity and diffusion processes in order to consider time-dependent coefficients. We are able to find the exact analytic solution of the creep experiment based on our new approach and we can compare it with the results obtained in [15].
Keywords: Scott-Blair model, fractional derivative, Mittag-Leffler function, creep, linear viscoelasticity, polymer rheology.
MSC2010: 26A33, 33E12, 74D05, 76A05.

.

1 Introduction

In the 1950's Scott-Blair in UK introduced a model in linear viscoelasticty that was intermediate between the elastic Hooke model and the fluid Newton model using the concept of derivative of non integer order $\nu \in (0,1)$, see for an historical perspective [13], As stated in the paper by Stiassnie [14], after several experimental contributions Scott-Blair told: *I gave up the work eventually, mainly because I could not find a definition of a fractional differential that would satisfy the mathematicians.*

However, since the times of Scott-Blair the fractional calculus, that is the mathematical discipline dealing with integrals and derivatives of non integer order, has been revisited and applied in several fields including linear viscoelasticity. For this purpose the reader is referred to the 1971 survey paper by Caputo and Mainardi [4] and subsequent contributions by Mainardi and colleagues, see *e.g.* [9, 8, 10] by using proper definitions of the Riemann-Liouville fractional calculus.

In a recent paper, Zhou et al. [15], studied the time-dependent properties of Glass Fiber Reinforced Polymers (GFRP) composites, by using a generalized Scott-Blair model with time-varying viscosity, showing a good agreement of the analytic results with the experimental data. Moreover, viscoelastic models based on time varying viscosity have been dealt recently by Pandey and Holm [12].

Motivated by these interesting studies, in this short note, we generalize the Scott-Blair model by using a different mathematical approach based on the application of Caputo fractional derivatives of a function with respect to a given function. In our view this approach can be useful especially to take into account time-variability of diffusion or viscosity coefficients in fractional models. For example a new fractional Dodson diffusion model based on this approach has been studied in [5]. The interest for the potential applications of this approach is proved by some recent studies, e.g. [1, 2, 3, 6]. The main aim of this preliminary and explorative study is to suggest an application in rheology of Caputo fractional derivatives of a function with respect to a given function.

In Section 2 we recall some results about the models introduced in Glass Fiber Polymers composites that in practice reduce to Scott-Blair models with time-varying viscosity. Then we discuss our novel approach, showing that it simple to find the explicit solution for the creep experiment. For readers' convenience we recall in Appendix the basic concepts about fractional derivatives with respect to a given function. Finally, Section 3 is devoted to discussions and conclusions.

2 Viscoelastic models with time-dependent degradation coefficient for polymer rheology

In a recent paper, Zhou et al. [15], studied the time-dependent property of Glass Fiber Reinforced Polymers (GFRP) composites, considering the time-dependent deformation at various stress level. In this paper, they use a fractional-type Maxwell rheology to describe the response of GFRP composites in a creep experiment. Their rheological model is based on the classical Scott Blair dashpot. Therefore, the constitutive equation is given by

$$\sigma(t) = \eta \tau_0^{\gamma-1} D_t^{\gamma} \epsilon(t), \quad \gamma \in [0,1], \tag{2.1}$$

where $\sigma(t)$ is the stress tensor, $\epsilon(t)$ the strain tensor, τ a relaxation time constant, η the viscosity coefficient and D_t^{γ} the Riemann-Liouville derivative of order γ. We recall that, this classical rheological model interpolates the pure solid behavior for $\gamma = 0$ and the Newtonian fluid for $\gamma = 1$. The interesting novelty of the model treated in [15] is

the appearence of a time-variable viscosity coefficient, given by

$$\eta(t) = (1 - d(t))\eta_0 = e^{\alpha t}\eta_0, \tag{2.2}$$

where $d(t)$ is a degradation variable and α is an empirical parameter associated to the damage evolution. This kind of fractional rheological model with time-dependent viscosity coefficient has been previously applied by the same authors to characterize damage growth in salt rock samples during creep tests in [16]. In a creep experiment $\sigma(t)$ is taken as a constant. In [15], the authors have find the explicit analytic solution of the creep experiment and it is given by

$$\epsilon(t) = \frac{\sigma}{\eta_0 \tau^{\gamma-1}} t^{\gamma} E_{1,1+\gamma}(\alpha t), \tag{2.3}$$

where

$$E_{1,1+\gamma}(t) = \sum_{k=0}^{\infty} \frac{t^k}{\Gamma(k+1+\gamma)}, \tag{2.4}$$

is a two-parameter Mittag-Leffler function. Observe that for $\gamma = 1$, we obtain

$$\epsilon(t) = \frac{\sigma}{\eta_0}(e^{\alpha t} - 1), \tag{2.5}$$

that coincides with the solution of (2.1) for $\gamma = 1$, η given by (2.2).

Here we use a different mathematical approach based on the application of fractional derivatives of a function with respect to another function (see [1] and Appendix A). Our model equation is given by

$$\sigma(t) = \eta_0 \tau_0^{\gamma-1} \left(e^{-\alpha t} D_t\right)^{\gamma} \epsilon(t). \tag{2.6}$$

The main idea is, therefore, to include the effect of the time-dependence of the viscosity coefficient in the definition of the fractional operator. In this way, we can include memory and time-variability in a single integro-differential operator. The operator appearing in (2.6), according to the general theory of fractional derivatives with respect to another function is defined by

$$\left(e^{-\alpha t} D_t\right)^{\gamma} \epsilon(t) = \frac{1}{\Gamma(1-\gamma)} \int_0^t \left(\frac{e^{\alpha\tau} - e^{\alpha t}}{\alpha}\right)^{-\gamma} \frac{d\epsilon(\tau)}{d\tau}\, d\tau. \tag{2.7}$$

Observing that

$$\left(e^{-\alpha t} D_t\right)^{\gamma} \left(\frac{e^{\alpha t} - 1}{\alpha}\right)^{\beta} = \frac{\Gamma(\beta+1)}{\Gamma(\beta+1-\gamma)} \left(\frac{e^{\alpha t} - 1}{\alpha}\right)^{\beta-\gamma}, \quad \alpha \neq 0, \beta > -1, \tag{2.8}$$

(see Appendix A, (A.3)), we are able to find the exact analytic solution for the case $\sigma(t) = \sigma_0$. It is given by

$$\epsilon(t) = \frac{1}{\Gamma(\gamma+1)} \frac{\sigma_0}{\eta_0 \tau_0^{\gamma-1}} \left(\frac{e^{\alpha t} - 1}{\alpha}\right)^{\gamma}. \tag{2.9}$$

Observe that, also in this case for $\gamma = 1$ we recover the classical solution related to a Newtonian fluid with time-dependent viscosity and for $\gamma = 0$ the solid behavior $\epsilon \sim \sigma_0/\eta_0$.

3 Conclusions

Fractional calculus has found relevant applications in rheology, see e.g. [10] for a review. In a recent paper Zhou et al. [15] revisited the classical Scott-Blair model including the time dependence of the degradation variable in the analysis of the rheology of Glass Fiber Reinforced Polymers. Here we suggest a different new mathematical approach to the generalized Scott-Blair model based on the application of Caputo fractional derivative of a function with respect to another function. We have shown the simplicity of this approach in order to find explicit solution to the model equation. Moreover, in our view this new approach can be applied in many problems in fractional viscoelasticity where viscosity coefficients can be time-dependent. Further consequences of this approach in viscoelasticity and experimental validation should be object of further research. Indeed every standard model in linear viscoelasticity needs the presence of dashpots in the Newton or Scott-Blair sense so in the next future we will consider the basic models of fractional viscoelasticity with Scott-Blair dashpots with a time varying viscosity.

Acknowledgments

The work of the authors has been carried out in the framework of the activities of the National Group of Mathematical Physics (INdAM-GNFM).

A Caputo fractional derivative of a function with respect to another function

Fractional derivatives of a function with respect to another function have been already known from the classical monograph by Kilbas et al. [7] (Section 2.5) and in a recent paper Almeida [1] has studied in detail the Caputo-type regularization of this fractional operator. Here we briefly recall the main definitions and properties, referring to [1] for a more complete discussion. We also observe that this approach has found some interesting applications in [2], [3], [5] and [6] .

Definition A.1. *Let $\nu > 0$, $I = (a, b)$ is the interval $-\infty \leq a < b \leq +\infty$, $f(t) \in C^1(I)$ an increasing function such that $f'(t) \neq 0$ for all $t \in I$, the fractional integral of a function g(t) with respect to another function $f(t)$ is given by*

$$I_{a^+}^{\nu,f} g(t) := \frac{1}{\Gamma(\nu)} \int_a^t f'(\tau)(f(t) - f(\tau))^{\nu-1} g(\tau) d\tau. \tag{A.1}$$

Observe that for $f(t) = t^{\alpha/\beta}$ we recover the definition of Erdélyi-Kober fractional integral that has recently foud many applications in various branches of physics and mathematics, see *e.g.* [11]. In the case of $f(t) = \ln t$ we have the Hadamard fractional integral and for $f(t) = t$, the Riemann-Liouville fractional integral (see [7]).

The corresponding Caputo-type evolution operator is given in the following definition

Definition A.2. *Let $\nu > 0$, $n \in \mathbb{N}$, $I = (a, b)$ is the interval $-\infty \leq a < b \leq +\infty$, $f(t), g(t) \in C^n(I)$ are two functions such that $f'(t) \neq 0$ for all $t \in I$, the Caputo derivative of the function $g(t)$ with respect to the function $f(t)$ is given by*

$$ {}^{C}\left(\frac{1}{f'(t)}\frac{d}{dt}\right)^{\nu} g(t) := I_{a^+}^{n-\nu,f}\left(\frac{1}{f'(t)}\frac{d}{dt}\right)^{n} g(t), \tag{A.2} $$

where $n = \lceil \nu \rceil$.

Notice that, we used a quite different notation with respect to the one adopted by Almeida in [1]. This has been done in order to underline that one can, somehow, regard these operators as the fractional power counterpart of the operators with time-varying coefficients, *i.e.* $\frac{1}{f'(t)}\left(\frac{\partial}{\partial t}\right)$.

A relevant property of the operator (A.2) is that if $g(t) = (f(t) - f(a))^{\beta-1}$ with $\beta > 1$, then (see Lemma 1 of [1])

$$ {}^{C}\left(\frac{1}{f'(t)}\frac{d}{dt}\right)^{\nu} g(t) = \frac{\Gamma(\beta)}{\Gamma(\beta-\nu)}(f(t) - f(a))^{\beta-\nu-1}. \tag{A.3} $$

As a consequence, the composition of the Mittag-Leffler function with the function $f(t)$, that is

$$ g(t) = E_{\nu}(\lambda(f(t) - f(a))^{\nu}) = \sum_{k=0}^{\infty} \frac{\lambda^k((f(t) - f(a))^{\nu k}}{\Gamma(\nu k + 1)}, \tag{A.4} $$

satisfies the equation

$$ {}^{C}\left(\frac{1}{f'(t)}\frac{d}{dt}\right)^{\nu} g(t) = \lambda g(t), \tag{A.5} $$

i.e. it is an eigenfunction of the operator ${}^{C}\left(\frac{1}{f'(t)}\frac{d}{dt}\right)^{\nu}$. Compositions of Mittag-Leffler functions with other functions can be potentially useful, as recently discussed by Almeida in [2]. The connection with integro-differential equations can give rigorous theoretical motivations for these studies.

References

[1] R. Almeida, A Caputo fractional derivative of a function with respect to another function, *Commun. Nonlinear Sci. Numer. Simulat.* **44** (2017), 460–481.

[2] R. Almeida, What is the best fractional derivative to fit data?, *Applicable Analysis and Discrete Mathematics* **11** No 2 (2017), 358–368.

[3] R. Almeida, A. B. Malinowska, M. T. Monteiro, Fractional differential equations with a Caputo derivative with respect to a kernel function and their applications, *Math. Meth. Appl. Sci.* **41** (2018), 336–352. DOI:10.1002/mma.4617

[4] M. Caputo, F. Mainardi, Linear models of dissipation in anelastic solids, *Rivista del Nuovo Cimento* (Ser.II) **1** (1971), 161–198.

[5] R. Garra, A. Giusti, F. Mainardi, The fractional Dodson diffusion equation: a new approach, *Ricerche di Matematiche*, published on line 17 January 2018, 11 pages; DOI:10.1007/s11587-018-0354-3 [E-print https://arxiv.org/pdf/1709.08994.pdf]

[6] M.Jleli, D. O'Regan, B. Samet, Some fractional integral inequalities involving m-convex functions, *Aequat. Math.* **91** (2017), 479–490/

[7] A. A. Kilbas, H. M. Srivastava, J. J. Trujillo, *Theory and Applications of Fractional Differential Equations*, Elsevier, Boston (2006).

[8] F. Mainardi, *Fractional Calculus and Waves in Linear Viscoelasticity*, Imperial College Press, London (2010), pp. 340.

[9] F. Mainardi, M. Tomirotti, Seismic pulse propagation with constant Q and stable probability distributions, *Annali di Geofisica* **40** (1997), 1311–1328. [E-print: http://arxiv.org/abs/1008.1341]

[10] F. Mainardi, G. Spada, Creep, relaxation and viscosity properties for basic fractional models in rheology, *The European Physical Journal, Special Topics* **193** (2011), 133–160. [E-print http://arxiv.org/abs/1110.3400] ,

[11] G. Pagnini, Erdélyi-Kober fractional diffusion, *Fractional Calculus and Applied Analysis* **15** No 1 (2012), 117–127.

[12] V. Pandey, S. Holm, Linking the fractional derivative and the Lomnitz creep law to non-Newtonian time-varying viscosity, *Phys. Rev E* **94** (2016), 032606/1–6. (2016)

[13] S. Rogosin, F. Mainardi, George William Scott Blair - the pioneer of fractional calculus in rheology, *Communications in Applied and Industrial Mathematics* **6** No 1 (2014), e-481, 20 pages; DOI: 10.1685/journal.caim.481; available at http://caim.simai.eu/index.php/caim/issue/view/48/ N.B. A larger version (22 pages) is posted as E-print at arXiv:1404.3295

[14] M. Stiassnie, On the application of fractional calculus on the formulation of viscoelastic models, *Appl. Math. Modelling,* **3** (1979), 300–302.

[15] H. W. Zhou, H. Y. Yi, L. Mishnaevsky, R. Wang, Z. Q. Duan, Q. Chen, Deformation analysis of polymers composites: rheological model involving time-based fractional derivative, *Mechanics of Time-Dependent Materials*, **21** No 2 (2017), 151-161.

[16] H. W. Zhou, C. P. Wang, L. Mishnaevsky, Z. Q. Duan, J. Y. Ding, A fractional derivative approach to full creep regions in salt rock *Mechanics of Time-Dependent Materials* **17** No 3 (2013), 413–425.