arXiv:cond-mat/0504292v1 [cond-mat.mtrl-sci] 12 Apr 2005

Twin Boundaries and Heat Capacity of a Crystal

V.N.Dumachev [1]

Voronezh Institute of the Ministry of Internal Affairs of the Russian Federation,
Voronezh, Russia

Abstract

The influence of twin boundaries on the heat capacity and diffuse scattering in a crystal is described within the framework of a macroscopic dynamic theory. ©2005 Pleiades Publishing, Inc.

Achievements of the modern nanotechnologies in the synthesis of structures of arbitrary dimensions set the important task of studying natural low-dimensional formations in crystals, such as dislocations and domain walls, and the influence of such objects on the mechanical and kinetic properties of materials. This paper shows that coherent twin boundaries can significantly influence the thermodynamic properties of crystals.

Consider an elastic continuous medium containing a defect that acts as the source of a plastic deformation field. A local change in position of the surface of this defect will modify the mismatch between the defect and environment. In the case of a planar defect, this is manifested by the motion of misfit dislocations. The resulting configurational or surface forces act so as to bring the defect boundary to an equilibrium state, while the mismatch becomes (due to inertial properties of the medium) a source of elastic waves. Considering the total deformation of the crystal u_{lm} in the presence of the structural defect as comprising the elastic ε_{lm} and plastic s_{lm} components, the Lagrangian of the elastic continuum can be written as

$$L = \frac{1}{2}\int d\mathbf{r}dt\left(\rho\left(\dot{u}_i\right)^2 - \left(u_{ik} - s_{ik}\right)\lambda_{iklm}\left(u_{lm} - s_{lm}\right)\right). \qquad (1)$$

Let us consider the coherent boundary as an independent object in the crystal possessing its own dynamical variable $\varsigma\left(\mathbf{r}_{||}, t\right)$ representing a deviation of the boundary relative to the habit plane. Then, writing the plastic deformation caused by this deviation as

[1]e-mail: dumv@comch.ru

$$s_{ij} = \varsigma\left(\mathbf{r}_{||}, t\right)\delta\left(z\right)\left[S_{ij}\right]$$

substituting this expression into Lagrangian (1), and considering variations over the dynamical variables $u_i\left(\mathbf{r}, t\right)$ and $\varsigma\left(\mathbf{r}_{||}, t\right)$, we eventually obtain a system of differential equations [1]

$$\begin{array}{l} \rho\ddot{u}_i - \lambda_{iklm}\partial^2_{kl}u_m + \partial_k\left(\lambda^s_{ik}\delta\left(z\right)\varsigma\left(\mathbf{r}_{||}, t\right)\right) = 0 \\ \left(\lambda^s_{ik}\partial_k u_m - \lambda^s\delta\left(z\right)\varsigma\left(\mathbf{r}_{||}, t\right)\right)_{z=0} = 0 \end{array}.$$

These equations have a self-consistent solution under the condition provided by the dispersion relation [2]

$$\frac{q_y^2 - \omega^2/c_t^2}{\sqrt{\mathbf{q}_{||}^2 - \omega^2/c_t^2}} + \frac{4q_x^2}{\omega^2/c_t^2}\left(\sqrt{\mathbf{q}_{||}^2 - \omega^2/c_l^2} - \sqrt{\mathbf{q}_{||}^2 - \omega^2/c_t^2}\right) = 0. \qquad (2)$$

Here, it is assumed that the habit plane of the boundary is perpendicular to the $0z$ axis, $\left[S_{ik}\right] = 1/2\left(n_i S_k + n_k S_i\right)$ is the offset of the plastic deformation tensor on the pas- sage through the boundary, $n_i = (0, 0, 1)$ is vector of the normal to the boundary, $S_i = (S_x, 0, 0)$ is the vector of the boundary displacement, and $\lambda^s = S_{ik}\lambda_{iklm}S_{lm} = S_{ik}\lambda^s_{ik}$. The roots of dispersion equation (2) determine a relation between the eigenvector $\mathbf{q}_{||}$ and the intrinsic frequency ω of bending oscillations of the boundary [3]: $\omega = \xi\left(\varphi\right)c_t\mathbf{q}_{||}$ (fig.1).

First, let us calculate the phonon heat capacity of a crystal [4]. The Einstein approximation for this prob lem stipulates a linear dependence of the wave fre quency ω on the wave vector $\mathbf{q}$. Using Eq. (2) it is also possible to take into account the influence of a nonlin ear dispersion related to the presence of a planar defect in the crystal studied. The number of field oscillators with the wavenumbers below $\mathbf{q}$ can be determined as

$$N\left(\omega\right) = \int\limits_0^{\mathbf{q}} d\mathbf{q}_{||} = \int\limits_0^{\omega/c_t\xi(\varphi)} qdqd\varphi = \frac{\omega^2}{2c_t^2}\int\limits_0^{\pi/2}\frac{d\varphi}{\xi^2\left(\varphi\right)} = \frac{\omega^2}{2c_t^2}\frac{\pi}{2}\Omega$$

where $\Omega \cong 1.074$. Then, the Debye frequency ω_0 for the bound phonon states is

$$\omega_0^2 = \frac{4Nc_t^2}{\Omega\pi} = \frac{\omega_\theta^2}{3\Omega},$$




Figure 1: Dependence of the $\xi = \omega/(c_t \mathbf{q}_{||})$ on angle $\varphi = Atan(S_y/S_x)$ and $\gamma = c_t/c_l$.

where ω_θ is the Debye frequency of the bulk waves. Such a considerable decrease in the Debye frequency of the twin boundary is related to softening of the phonon modes accompanying the displacement of atoms in the crystal lattice along the direction of the shear vector S_i.

Using the dispersion relation (2), we obtain the average energy of localized oscillations at low temperatures ($T << T_0$) in the Debye approximation:

$$\langle E_0 \rangle = \int_0^\infty \frac{\hbar\omega}{exp\left(\hbar\omega/kT\right) - 1} dN\left(\omega\right) = \frac{\hbar}{c_t^2}\frac{\pi}{2}\Omega\omega_0^3 2\zeta\left(3\right) = \frac{1}{\sqrt{3\Omega}}\left\langle E_\theta \right\rangle,$$

where $\zeta\left(3\right) = 1.202057$ is the Riemann zeta function and $\langle E_\theta \rangle$ is the average energy of the bulk waves in the defect-free crystal.

The heat capacity is defined as $c_v^0 = \partial E/\partial T$. However, in our case, it is convenient to calculate the ratio of this quantity to the heat capacity of the defect-free crystal:

$$\frac{c_v^0}{c_v^\theta} = \frac{\partial E_0/\partial T}{\partial E_\theta/\partial T} = \frac{\partial E_0}{\partial E_\theta} = \frac{1}{\sqrt{3\Omega}} \text{ or } c_v^0 = \frac{c_v^\theta}{\sqrt{3\Omega}}.$$

Evidently, a decrease in the heat capacity is related to two factors: (i) a threefold decrease in the number of bulk oscillatory modes of the crystal and

(ii) the anisotropic velocity of the surface wave packet propagating along the twin boundary.

The presence of a single coherent twin boundary in the crystal does not influence the positions of electron or X-ray diffraction reflections.An ensemble of parallel twins will only lead to the appearance of superstructure satellites. However, a change in the spectrum of crystal oscillations in the vicinity of the twin boundary leads to a significant decrease in the total intensity of the Born scattering as a result of an increase in the diffuse scattering component [5].

Considering the thermal oscillations of atoms at the twin boundary as a system of elastic standing waves obeying relation (2), the influence of these oscillations on the intensity of selective maxima can be described in terms of the DebyeWaller factor

$$2M = \frac{16\pi^2 \langle u^2 \rangle}{3} \frac{sin^2\vartheta}{\lambda^2}.$$

Here, the mean square deviation of atoms in the crystal can be expressed via the above relation for the average energy as

$$\left\langle u_0^2 \right\rangle = \int_0^\infty \frac{E_0}{\omega^2} dN(\omega) = \int_0^\infty \frac{\hbar}{exp\left(\hbar\omega/kT\right) - 1} \frac{dN(\omega)}{\omega} = \sqrt{3\Omega} \left\langle u_\theta^2 \right\rangle.$$

Similar to the case considered above, the presence of a coherent twin boundary in the crystal changes the observed effect by a factor of $\sqrt{3\Omega} \approx 1.8$.

References

1. A. M. Roshchupkin, V. N. Nechaev, and V. N. Dumachev, Izv. Ross. Akad. Nauk, Ser. Fiz. 59 (10), 108 (1995).

2. V. N. Nechaev and A. M. Roshchupkin, Sov. Phys. Solid State 31,1321 (1989).

3. L. D. Landau and E. M. Lifshitz, Course of Theoretical Physics, Vol. 7: Theory of Elasticity (Pergamon, New York, 1986).

4. Ya. P. Terletskii, Statistical Physics, (3rd Edition) (North-Holland, Amsterdam, 1971).

5. V. I. Iveronova and G. P. Revkevich, Theory of X-Ray Scattering (Moscow State University, Moscow, 1978) [in Russian].

Translated by P. Pozdeev